

White Oak Blanks

Classic White Oak - A Side

Thickness/Stärke: 4/4" hit or miss 25,4 mm
 Width/Breite: 3"-8" ripped after KD to fixed widths/geschnitten nach KD in Fixbreiten
 Length/Länge: 5'-14' cut to fixed lengths/gekappt in Fixlängen

The A-Side is a high quality product allowing limited sap, defects and color variations. Limited end-splits are also allowed. If wane appears, it will come out in the milling process.

Classic White Oak - B Side

Measurement like the A-Side.

The B-Side of the classic blank allows more defects than the A-Side. Sap and color are not defect. Limited checking, wane and end splits are allowed.

Contemporary White Oak - A Side

Thickness/Stärke: 4/4" hit or miss 25,4 mm
 Width/Breite: 3"-8" ripped after KD to fixed widths/geschnitten
 nach KD in Fixbreiten
 Length/Länge: 4'-14' cut to fixed lengths/gekappt in Fixlängen

The A-side allows large knots that can sometimes be filled. If a knot cannot be filled high quality cuttings can be obtained. Sap and color are not a defect. Limited end-splits are allowed. If wane appears, it will come out in the milling process.

Contemporary White Oak - B Side

Measurement like the A-Side.

The B-side of the "Contemporary" blank allows more knots and varied defects (such as checking) than the A-side. Sap and color are not a defect. Limited end-splits and limited wane are allowed.

Traditional White Oak - A Side

Thickness/Stärke: 4/4" hit or miss 25,4 mm
 Width/Breite: 3"-8" ripped after KD to fixed widths/geschnitten nach KD in Fixbreiten
 Length/Länge: 3'-14' cut to fixed lengths/gekappt in Fixlängen

The A-side allows many knots, sound (can be filled) and unsound (must be cut out). The cuttings will be shorter than the "Contemporary" product. Sap and color are not a defect. End-splits are allowed. If wane appears it will come out in the milling process.

Traditional White Oak - B Side

Measurement like the A-Side

The B-Side of the traditional blank allows more knots and varied defects than the A-Side. Sap and color are not a defect. End-splits and limited wane are allowed.

Colonial White Oak - A Side

Thickness/Stärke: 4/4" hit or miss 25,4 mm
Width/Breite: 3"-8" ripped after KD to fixed widths/
geschnitten nach KD in Fixbreiten
Length/Länge: 3'-14' cut to fixed lengths/gekappt in Fixlängen

The A-side allows more unsound defects than the "Traditional" product as well as shorter cuttings. Sap and color are not a defect. End-splits are allowed. If wane appears, it will come out in the milling process.

Colonial White Oak - B Side

Measurement like the A-Side

The B-Side of the traditional blank allows more knots and varied defects than the A-Side. Sap and color are not a defect. End-splits and limited wane are allowed.